

## TEST

## RESULT

MOISTURE CONTENT

BELOW 12%

NO DE-LAMINATION AFTER BOILING

72 HOURS

ADHESION OF PLYS

EXCELLENT

MODULUS OF ELASTICITY

(N/MM<sup>2</sup>) > 6000

MODULUS OF RUPTURE

(N/MM<sup>2</sup>) > 5000

SPECIFIC GRAVITY

MORE THAN 0.65

SCREW HOLDING STRENGTH

MORE THAN 100 KGS

NAIL HOLDING STRENGTH  
MORE THEN

50 KGS.

WATER ABSORPTION

1%