

# SAMRAT ECO PLY

TEST	RESULT
MOISTURE CONTENT	5% TO 10%
GLUE SHEER STRENGTH (DRY STATE)	MORE THAN 1350 N
ADHESION OF PLYS	EXCELLENT
WATER RESISTANCE TEST	MORE THAN 1000 N
MYCOLOGICAL TEST	MORE THAN 1000 N
BOILING WATER TEST	NO DELAMINATION AFTER BOILING FOR 72 HRS.
GLUE ADHESION	EXCELLENT
SPECIFIC GRAVITY	0.70 TO 0.75
SCREW HOLDING STRENGTH	MORE THAN 200 KGS.
NAIL HOLDING STRENGTH	MORE THAN 50 KGS.
WATER ABSORPTION	LESS THAN 3 %