

SAMRAT PINNACLE PLY

TEST	RESULT
MOISTURE CONTENT	BELOW 12%
NO DE-LAMINATION AFTER BOILING	72 HOURS
ADHESION OF PLYS	EXCELLENT
MODULUS OF ELASTICITY	(N/MM2) > 6000
MODULUS OF RUPTURE	(N/MM2) > 5000
SPECIFIC GRAVITY	MORE THAN 0.65
SCREW HOLDING STRENGTH	MORE THAN 100 KGS
NAIL HOLDING STRENGTH MORE THEN	50 KGS.
WATER ABSORPTION	1%